

## Arrowglass VI

### Uses & Description

Arrowglass VI is manufactured with a heavyweight fiberglass mat containing heat-cured resinous binders. The high strength glass mat is saturated with TYPE IV asphalt, giving Arrowglass VI excellent strength and weathering characteristics, as well as a uniform porosity for ease in application.

Arrowglass VI is a ply sheet used in hot mopped roofing applications and may be the basic ply sheet used in all smooth and gravel surfaced roofing systems requiring the ASTM D-2178 TYPE VI felt

Meets Florida Approval BFL # 2074



### Specifications

<b>ASTM</b>	D 2178-04 TYPE VI
<b>UL</b>	TYPE G2
<b>BREAKING STRENGTH, lbf/in (kN/m)</b>	
longitude	60 (10.5)
transverse	60 (10.5), min
<b>PLIABILITY, @ 77°F and 50% RH; 1/2" radius (pass/fail)</b>	
longitude	PASS
traverse	PASS
<b>NET DRY MASS OF ASPHALT-IMPREGNATED GLASS FELT, lbs/100 ft2 (g/m2)</b>	
average of all rolls	
-nonlinearly parting agent	6.2 (303)
-mineral parting agent	7.0 (342)
individual rolls	6.0 (293)
<b>MOISTURE, at time of manufacturing</b>	1.0%, max
<b>MASS OF DESATURATED GLASS FELT, lbs/100 ft2</b>	1.9 (93), min
<b>ASPHALT, lbs/100 ft2 (g/m2)</b>	3.0 (146), min
<b>ASH</b>	70% to 88%
<b>PARTING AGENT AND STABILIZER, lbs/100 ft2 (g/m2)</b>	3.0 (146), max